

MINOAN GREY

TECHNICAL SPECIFICATIONS

Apparent density	(EN 1936), kg/m ³	2770
Open porosity	(EN 1936), % vol.	2,2
Water absorption at atmospheric pressure	(EN 13755), % wt.	0,23
Flexural strength under concentrated load	(EN 12372), MPa	8,3
Abrasion resistance	(EN 14157 - B), mm ³	16780
Frost resistance	(EN 12371)	
Flexural strength under concentrated load (EN 12372) after 48 frost resistance cycles, MPa		6,5
Uniaxial compressive strength	(EN 1926), MPa	184
Impact Strength	(UNI-U 32.07.248.0 / rupture energy EN 14158) Joule	4